
Halton Final DFTs

Created: 2018-10-28 14:10:20
PosiTector SmartLink S/N: 786962
Probe Type: PosiTector 6000 FS
Probe S/N: 258301
CAL Cal 15

Coating system is
SSPC SP 10 near white blast
Wasser Mio Zinc 3-5 mils
SW Macropoxy 646HS 4-6 mils
Ameron Amershield 3-5 mils

Minimum system DFT 10 mils

The coating was fully inspected.
It is uniform and monolithic.
It meets the specs as issued and is approved.

Julian Hay.
NACE Coating Inspector (Level 3) #7382



Summary

| | # | x | σ | ↓ | ↑ |
|------------------|----|-------|----------|------|------|
| Thickness (Mils) | 51 | 14.55 | 2.52 | 10.2 | 22.5 |

Halton Final DFTs Readings

| # | Thickness (Mils) |
|----|---------------------|
| 1 | 15.5 |
| 2 | 13.8 |
| 3 | 16.5 |
| 4 | 18.5 |
| 5 | 17.1 |
| 6 | 13.2 |
| 7 | 13.1 |
| 8 | 16.9 |
| 9 | 11.7 |
| 10 | 12.6 |
| 11 | 18.9 |
| 12 | 19.3 |
| 13 | 16.3 |
| 14 | 11.6 |
| 15 | 13.1 |
| 16 | 14.3 |
| 17 | 13.4 |
| 18 | 11.3 |
| 19 | 13.1 |
| 20 | 12.3 |
| 21 | 13.4 |
| 22 | 11.5 |
| 23 | 17.1 |
| 24 | 16.3 |
| 25 | 17.7 |
| 26 | 13.0 |
| 27 | 12.9 |
| 28 | 14.5 |
| 29 | 14.4 |
| 30 | 16.9 |
| 31 | 14.3 |
| 32 | 16.3 |
| 33 | 17.3 |
| 34 | 12.6 |
| 35 | 11.1 |
| 36 | 16.3 |
| 37 | 16.8 |
| 38 | 14.1 |
| 39 | 13.3 |
| 40 | 15.1 |
| 41 | 12.7 |
| 42 | 17.1 |
| 43 | 13.7 |
| 44 | 12.4 |
| 45 | 15.1 |
| 46 | 10.7 |
| 47 | 10.2 |
| 48 | 12.6 |
| 49 | 13.5 |
| 50 | 22.5 |
| 51 | 14.2 |

